

Crack Buster® Pro Crack Prevention Mat Underlayment



1. Product Name

Crack Buster® Pro Crack Prevention Mat Underlayment

2. Product Description

A self-bonding, fabric reinforced, asphaltic membrane that isolates ceramic and natural stone tile from cracks in the substrate. Crack Buster® Pro is ANSI A118.12 compliant as a crack isolation membrane and reduces sound transmission through the tile assembly.

Key Features

- Extra heavy-duty rated for both full and partial coverage applications
- Easy peel & stick application that provides secure bonding for all types of ceramic, natural stone, and terrazzo tile
- Elastomeric - Reduces crack transmission -- up to 3/8" (9.5 mm) -- in tile and stone floors
- Provides IIC sound reduction up to 18 dB
- Reduces downtime allowing immediate installation of tile

Suitable Substrates

- Concrete, cement mortar, masonry
- Cement Backerboard
- Exterior Plywood and OSB (interior, dry areas only)
- Exterior Decks - Contact Technical Services
- Post-Tension Concrete - Contact Technical Services
- Lightweight Concrete (min. 2000 psi compressive strength)
- Gypsum-Based cement topping (min. 2000 psi compressive strength)
- Existing ceramic tile and resilient flooring

Composition of Product

Crack Buster® Pro is an elastomeric, fabric-reinforced mat underlayment, with modified asphalt and a polyurethane adhesive.

Benefits of Product in the Installation

- Extra heavy-duty rating for installation within diverse substrates.
- Exceeds ANSI A118.12 standards for crack isolation material.
- Eliminates crack transmission in tile and stone floors.
- Easy and quick self-adhesive installation reduces downtime for tile and stone installation.
- Sound transmission reduction (IIC) using A118.13 section 5.3 is 18 dB

Limitations to the Product

- Do not bond directly to hardwood, Luan plywood, particle board, parquet, cushion or sponge-back vinyl flooring, metal, fiberglass, plastic or OSB panels.
- Do not use as a wear surface.
- When setting glass tile larger than 6" Å— 6" (15 Å— 15 cm), contact Custom's Technical Services for recommendations.
- When setting dimensional stone larger than 12" Å— 12" (30 Å— 30 cm), contact Custom's Technical Services for recommendations regarding subfloor deflection requirements.

Packaging

36" x 75' (.91 x 23 M) Rolls

3. Technical Data

Applicable Standards

American National Standards Institute (ANSI) ANSI A108.01, A108.17, A118.12 and A118.13 American National Standards for the Installation of Ceramic Tile ASTM International (ASTM)

- ASTM C627 Standard Test Method for Evaluating Ceramic Floor Tile Installation Systems Using the Robinson-Type Floor Tester
- ASTM D638 Standard Test Method for Tensile Properties of Plastics

Tile Council of North America (TCNA) TCNA Handbook for Ceramic Tile Installation, TCNA Method EJ171, F125 & F125A

Technical Chart

Property	Test Method	Typical Results
Thickness		0.04€ (1 mm)
Weight per Roll		65 lb (29.48 kg)
Weight per ft2		.3 lb (ft2)
Roll Dimensions		36" x 75"
Robinson Floor Test	ASTM C627	Extra heavy duty
Elongation	ASTM D412	1200%
Bacteria and Fungus Resistance	ANSI A118.12	No growth
Peel Adhesion	ASTM D1000	Over 10 lb/in
Sound Reduction	ANSI A118.13	18dB

Environmental Consideration

Custom® Building Products is committed to environmental responsibility in both products produced and in manufacturing practices. Use of CrackBuster® Pro can contribute to LEED® certification.

4. Instructions

General Surface Prep

Exterior and wet areas must have proper sloping to drains. All surfaces must be structurally sound, clean, dry and free from contaminants that would prevent a good bond. Newly prepared concrete must be troweled smooth and textured to a fine broom finish and cured for 28 days. Existing surfaces must be scarified and leveled, and all defects must be repaired. Cracks exceeding 1/8" (3 mm) should be treated in accordance with TCNA F125 or TCNA F125A.

Bonding to Gypsum Surfaces

Gypsum substrates must exceed 2000 psi (13.8 MPa) and must be fully sealed using Peel & Stick Primer.

Bonding to Plywood and OSB Surfaces

Plywood floors, including those under resilient flooring, must be structurally sound and must meet all ANSI and deflection requirements. For questions about proper subfloor installation, call

Crack Buster® Pro Crack Prevention Mat Underlayment

Custom® Building Products.

Bonding to Cutback Adhesive

Thick accumulations and powdery, brittle or weak cut back adhesive layers must be removed. Use extreme caution, as adhesives may contain asbestos fibers. Do not sand or grind the adhesive residue, as harmful dust may result. Never use adhesive removers or solvents, as they weaken or soften the adhesive and may cause it to penetrate into the concrete. The remaining residue should be no thicker than a coat of paint and should be almost transparent. Always install an adequate number of properly located test areas.

Movement Joint Placement

Expansion joints and cold joints, as described in ANSI A108.01, should never be bridged with setting material. They must be brought through the tile work and filled with an appropriate elastomeric sealant, such as Custom's 100% Silicone. Contact Custom's Technical Services for the proper treatment of control or saw cut joints. Refer to TCNA EJ171, F125 & F125A.

Application of Product

Application of Primer

For proper adhesion and optimal bond, prime the substrate with Peel & Stick Primer. Using a paint brush, short-nap roller or soft-push broom, apply an even coat and allow it to dry until tacky to the touch, about 30-40 minutes. When the primer does not transfer to your finger, the surface is ready for application of CrackBuster® Pro.

Full Floor Application

With the release sheet still attached, unroll and position the membrane over the area to be treated and cut the membrane to the appropriate length. Roll up half of the cut membrane, leaving the other half in position. Cut the release sheet from the rolled-up portion of the membrane and pull the membrane into position, exposing and unrolling the self-stick portion. Return to the unrolled portion of the membrane and follow the same procedure. Check the positioning; smooth wrinkles and bubbles with a flat trowel and roll with a 50 lb (23 kg) roller or apply 50 lb (23 kg) of pressure with a hand roller to ensure complete contact with the substrate. Air pockets and wrinkles should be slit then smoothed with a roller or the flat side of a trowel. Align subsequent sheets and butt-join the seams tightly but do not overlap them. Clean tools with soap and warm water.

Crack Isolation Application

With the release sheet still attached, premeasure and cut the membrane to the desired length. The membrane should extend 6"-8" (15-20 cm) beyond the length of the crack in both directions and should extend beyond both sides of the crack and at least 3 times the dimension of the tile used. Reroll the membrane and center it over the crack. Remove about 2" (5 cm) of release paper and apply it firmly to the substrate. Remove the rest of the release paper, exposing and unrolling the self-stick portion of the membrane. Secure the membrane to the substrate with a 50 lb (23 kg) roller or equivalent heavy pressure from a hand roller or flat trowel. Remove fresh adhesive from tile surfaces with a damp cloth. Clean tools in warm soapy water.

Cleaning of Equipment

Clean tools and hands with water before material dries.

Storage

Store and transport in a cool dry area.

Health Precautions

Wear impervious gloves and eye protection while using this product. Avoid contact with eyes or prolonged contact with skin. Wash

thoroughly after handling. If eye contact occurs, rinse cautiously with water for several minutes, remove contact lenses if easy to do: continue rinsing. Immediately seek medical advice if symptoms are significant or persist. Do not take internally. KEEP OUT OF REACH OF CHILDREN.

Conformance to Building Codes

Installation must comply with the requirements of all applicable local, state and federal code jurisdictions.

5. Size & Availability

Item Code	Size	Package
CBMP36	36" x 75' (91.5 cm x 23 M)	Roll

6. Product Warranty

Crack Buster® Pro is eligible for Custom® Building Products Lifetime Installations Systems Warranty. Custom® Building Products warrants to the original consumer purchaser that its product shall be free from defects in material and workmanship under normal and proper usage for a period of one year following the date of original purchase. Custom's® sole liability under this warranty shall be limited to the replacement of the product. Some states, countries or territories do not allow the exclusion or limitation of incidental or consequential damages, so the above limitation or exclusion may not apply to you. This warranty will not extend to any product which has been modified in any way or which has not been used in accordance with Custom's® printed instructions. Custom® makes no other warranties either expressed or implied. This warranty gives you specific legal rights, and you may have other rights that vary from state to state or from one country/territory to another.

7. Product Maintenance

Properly installed product requires no special maintenance.

8. Technical Services Information

For technical assistance, contact Custom® Building Products.

9. Filing System

Additional product information is available from the manufacturer upon request.

Related Products

Peel & #038; Stick Primer

Crack Buster® Pro Crack Prevention Mat Underlayment

Coverage Chart